

METAL SOLUTIONS

EOS Titanium Ti64ELI

Material Data Sheet

EOS TITANIUM Ti64ELI

EOS Titanium Ti64ELI has a chemical composition and corresponding to ASTM F136 and ASTM F3001. Ti64ELI is well-known light alloy, characterized by having excellent mechanical properties and corrosion resistance combined with low specific weight and biocompatibility. This material is ideal for many high-performance applications. Parts built with EOS Titanium Ti64ELI powder can be machined, shot-peened and polished in asbuilt and heat treated states. Due to the layerwise building method, the parts have a certain anisotropy.

MAIN CHARACTERISTICS

- Excellent mechanical properties and corrosion resistance
- Low weight and biocompatibility

TYPICAL APPLICATIONS

- Parts for medical industry


The EOS Quality Triangle

EOS uses an approach that is unique in the AM industry, taking each of the three central technical elements of the production process into account: the system, the material and the process. The data resulting from each combination is assigned a Technology Readiness Level (TRL) which makes the expected performance and production capability of the solution transparent.

EOS incorporates these TRLs into the following two categories:

- Premium products (TRL 7-9): offer highly validated data, proven capability and reproducible part properties.
- Core products (TRL 3 and 5): enable early customer access to newest technology still under development and are therefore less mature with less data.


All of the data stated in this material data sheet is produced according to EOS Quality Management System and international standards



POWDER PROPERTIES

Powder Chemical Composition (wt.-%)

Element	Min.	Max.
Al	5.5	6.5
V	3.5	4.5
O	-	0.13
N	-	0.05
C	-	0.08
H	-	0.015
Fe	-	0.25
Y	-	0.005
Other Elements Each	-	0.1
Other Elements Total	-	0.4
Ti	Balance	



Powder Particle Size

GENERIC PARTICLE SIZE DISTRIBUTION	25 - 55 µm
------------------------------------	------------

HEAT TREATMENT

Steps

800 °C for 2 hours in argon inert atmosphere

HEADQUARTERS

EOS GmbH
Electro Optical Systems

Robert-Stirling-Ring 1
82152 Krailling / Munich
Germany

Tel.: +49 89 893 36-0
Email: info@eos.info
URL: www.eos.info

This powder has not been developed, tested or certified as a medical device according to Directive 93/42/EEC (MDD) or Regulation (EU) 2017/745 (MDR) and is not intended to be used as a medical device, in particular for the purposes specified in Art. 2 No. 1 MDR. Insofar as you intend to use the powder as raw material for the manufacture of pharmaceutical products or medical devices (e.g. as raw material which as a material must meet the requirements of Annex 1, Chapter II MDR), the responsibility and liability for all analyses, tests, evaluations, procedures, risk assessments, conformity assessments, approval and certification procedures as well as for all other official and regulatory measures required for this purpose shall lie solely with you both with regard to the pharmaceutical product and/or medical device manufactured by you and with regard to the properties, suitability, testing, evaluation, risk assessment, other requirements for use of the powder as raw material. In this respect, the limitations of liability pursuant to our General Terms and Conditions and the system sales or material contracts shall apply.

Part properties are provided for information purposes only and EOS makes no representation or warranty, and disclaims any liability, with respect to actual part properties achieved. Part properties are dependent on a variety of influencing factors and therefore, actual part properties achieved by the user may deviate from the information stated herein. This document does not on its own represent a sufficient basis for any part design, neither does it provide any agreement or guarantee about the specific properties of a material or part or the suitability of a material or a part for a specific application.

The achievement of certain part properties as well as the assessment of the suitability of this material for a specific purpose is the sole responsibility of the user. Any information given herein is subject to change without notice.

Status as of 03.09.2024. Subject to technical modifications. EOS is certified according to ISO 9001.

EOS®, Additive Minds®, Alumide®, AMQ®, CarbonMide®, DirectMetal®, DMLS®, EOSAME®, EOSINT®, EOSIZE®, EOSPACE®, EOSPRINT®, EOSTATE®, EOSTYLE®, FORMIGA®, LaserProFusion®, PA 2200®, PrimeCast® and PrimePart® are registered trademarks of EOS GmbH Electro Optical Systems in some countries. For more information visit www.eos.info/trademarks.