

POLYMER SOLUTIONS

PA 2210 FR

Material Data Sheet

PA 2210 FR

Product Description

PA 2210 FR is a composition on the basis of polyamide 12 and a halogen-free flame retardant. With its good mechanical properties and its outstanding fire properties it is mainly used in the electrical and electronics industry. PA 2210 FR is certified by Underwriters Laboratories (UL). Safety and quality are continuously tested by a third-party to ensure ongoing compliance, with an UL Recognized Component Mark on the product label. A growing market are railway applications, as PA 2210 FR fulfills several requirement sets according to EN 45545-2, the European railway standard for fire protection. The material is also used in aerospace industry, flammability compliance according to FAR 25.853 is tested for every material batch.

MAIN CHARACTERISTICS

- Flame-retardant
- Halogen-free
- Fire classification UL 94/V-0
- UL certified - [View Blue Card](#)
- Fire classification FAR 25.853

TYPICAL APPLICATIONS

- Electrical and electronic parts, e. g. housings
- Railway interiors, e. g. ventilation ducts
- Aircraft interiors, e. g. air valves

MECHANICAL PROPERTIES	DRY / CONDITIONED	UNIT	TEST STANDARD
Tensile Modulus			ISO 527-1/-2
X Orientation	2500 / 2400	MPa	
Y Orientation	2500 / 2400	MPa	
Z Orientation	2300 / 2200	MPa	
Tensile Strength			ISO 527-1/-2
X Orientation	46 / 43	MPa	
Y Orientation	46 / 43	MPa	
Z Orientation	41 / 38	MPa	
Strain at Tensile Strength			ISO 527-1/-2
X Orientation	4 / 6	%	
Y Orientation	4 / 6	%	
Z Orientation	3 / 4	%	
Strain at Break			ISO 527-1/-2
X Orientation	4 / 7	%	
Y Orientation	4 / 7	%	
Z Orientation	3 / 4	%	
Flexural Modulus			ISO 178
X Orientation	2300 / -	MPa	
Flexural Strength			ISO 178
X Orientation	65 / -	MPa	

THERMAL PROPERTIES	DRY / CONDITIONED	UNIT	TEST STANDARD
Melting Temperature	185	°C	ISO 11357-1/-3
Temperature of Deflection under Load 1.80 MPa			ISO 75-1/-2
X Orientation	95	°C	
Z Orientation	108	°C	
Temperature of Deflection under Load 0.45 MPa			ISO 75-1/-2
X Orientation	165	°C	
Z Orientation	170	°C	
Flammability			CS 25 / JAR25 / FAR 25 § 25-853
Test Passed, 12s ignition time	1.7	mm	
Test Passed, 12s ignition time	2.0	mm	
Smoke Density			ABD 0031 (Issue:F), method: AITM 2.0007
Test Passed	1.7	mm	
Test Passed	2.0	mm	
Toxicity			ABD 0031 (Issue:F), method: AITM 3.0005
Test Passed	1.7	mm	
Test Passed	2.0	mm	
Burning Behavior, 0.75 mm nom. Thickness	HB	class	ANSI/UL 94, IEC 60695-11-10, -20
Thickness Tested	0.75	mm	
Blue Card Available	Yes		
Burning Behavior, 3.0 mm nom. Thickness	V-0	class	ANSI/UL 94, IEC 60695-11-10, -20
Thickness Tested	3.0	mm	
Blue Card Available	Yes		

ELECTRICAL PROPERTIES	DRY / CONDITIONED	UNIT	TEST STANDARD
Comparative Tracking Index CTI			IEC 60112
X Orientation	- / 425		
Y Orientation	- / 425		
Z Orientation	- / 450		
Electric Strength			IEC 60243-1
X Orientation	- / 18.1	kV/mm	
Y Orientation	- / 18.1	kV/mm	
Volume Resistivity			IEC 62631-3-1
X Orientation	- / 1E15	Ohm•m	
Y Orientation	- / 1E15	Ohm•m	
Surface Resistivity			IEC 62631-3-12
X Orientation	- / 1E14	Ohm	
Y Orientation	- / 1E14	Ohm	
Dissipation Factor 100 Hz			IEC 62631-2-1
X Orientation	- / 1013	E-4	
Y Orientation	- / 1013	E-4	
Dissipation Factor 1 MHz			IEC 62631-2-1
X Orientation	- / 691	E-4	
Y Orientation	- / 691	E-4	
Relative Permittivity 100 Hz			IEC 62631-2-1
X Orientation	- / 3.39		
Y Orientation	- / 3.39		
Relative Permittivity 1 MHz			IEC 62631-2-1
X Orientation	- / 2.25		
Y Orientation	- / 2.25		

OTHER PROPERTIES	VALUE	UNIT	TEST STANDARD
Density	1.06	g/cm ³	ISO 1183-1
Powder Color	white	-	-
Components Color	white	-	-

HEADQUARTERS

EOS GmbH
Electro Optical Systems

Robert-Stirling-Ring 1
82152 Krailling / Munich
Germany

Tel.: +49 89 893 36-0
Email: info@eos.info
URL: www.eos.info

This powder has not been developed, tested or certified as a medical device according to Directive 93/42/EEC (MDD) or Regulation (EU) 2017/745 (MDR) and is not intended to be used as a medical device, in particular for the purposes specified in Art. 2 No. 1 MDR. Insofar as you intend to use the powder as raw material for the manufacture of pharmaceutical products or medical devices (e.g. as raw material which as a material must meet the requirements of Annex 1, Chapter II MDR), the responsibility and liability for all analyses, tests, evaluations, procedures, risk assessments, conformity assessments, approval and certification procedures as well as for all other official and regulatory measures required for this purpose shall lie solely with you both with regard to the pharmaceutical product and/or medical device manufactured by you and with regard to the properties, suitability, testing, evaluation, risk assessment, other requirements for use of the powder as raw material. In this respect, the limitations of liability pursuant to our General Terms and Conditions and the system sales or material contracts shall apply.

Part properties are provided for information purposes only and EOS makes no representation or warranty, and disclaims any liability, with respect to actual part properties achieved. Part properties are dependent on a variety of influencing factors and therefore, actual part properties achieved by the user may deviate from the information stated herein. This document does not on its own represent a sufficient basis for any part design, neither does it provide any agreement or guarantee about the specific properties of a material or part or the suitability of a material or a part for a specific application.

The achievement of certain part properties as well as the assessment of the suitability of this material for a specific purpose is the sole responsibility of the user. Any information given herein is subject to change without notice.

Status as of 03.09.2024. Subject to technical modifications. EOS is certified according to ISO 9001.

EOS®, Additive Minds®, Alumide®, AMQ®, CarbonMide®, DirectMetal®, DMLS®, EOSAME®, EOSINT®, EOSIZE®, EOSPACE®, EOSPRINT®, EOSTATE®, EOSTYLE®, FORMIGA®, LaserProFusion®, PA 2200®, PrimeCast® and PrimePart® are registered trademarks of EOS GmbH Electro Optical Systems in some countries. For more information visit www.eos.info/trademarks.