

POLYMER SOLUTIONS

PA 2241 FR

Material Data Sheet

PA 2241 FR

Product Description

PA 2241 FR is a white polyamide 12 powder for processing in laser sintering systems, which contains a halogen-based flame retardant. Due to its recyclability the material is very cost-efficient compared to other flame-retardant materials on the market. The additively manufactured parts show good tensile strength and are suited to be used for aircraft interior applications, e.g., ventilation ducts and exhaust valves.

MAIN CHARACTERISTICS

- Flame-retardant
- Halogen-based flame retardant
- Refreshable

TYPICAL APPLICATIONS

- Aircraft interior parts, e.g., ventilation ducts, exhaust valves or brackets

MECHANICAL PROPERTIES	DRY / CONDITIONED	UNIT	TEST STANDARD
Tensile Modulus			ISO 527-1/-2
X Orientation	1900 / 1600	MPa	
Y Orientation	1900 / 1600	MPa	
Z Orientation	1900 / 1600	MPa	
Tensile Strength			ISO 527-1/-2
X Orientation	49 / 44	MPa	
Y Orientation	49 / 44	MPa	
Z Orientation	46 / 41	MPa	
Strain at Tensile Strength			ISO 527-1/-2
X Orientation	7 / 11	%	
Y Orientation	7 / 11	%	
Z Orientation	6 / 6	%	
Strain at Break			ISO 527-1/-2
X Orientation	15 / 22	%	
Y Orientation	15 / 22	%	
Z Orientation	6 / 9	%	

THERMAL PROPERTIES	DRY / CONDITIONED	UNIT	TEST STANDARD
Melting Temperature	185	°C	ISO 11357-1/-3
Temperature of Deflection under Load 1.80 MPa			ISO 75-1/-2
X Orientation	84	°C	
Temperature of Deflection under Load 0.45 MPa			ISO 75-1/-2
X Orientation	154	°C	
Flammability			CS 25 / JAR25 / FAR 25 § 25-853
Test Passed, 12s ignition time	1.0	mm	
Test Passed, 12s ignition time	1.5	mm	
Test Passed, 12s ignition time	2.0	mm	
Test Passed, 60s ignition time	1.0	mm	
Test Passed, 60s ignition time	1.5	mm	
Test Passed, 60s ignition time	2.0	mm	
Smoke Density			ABD 0031 (Issue:F), method: AITM 2.0007
Test Passed	1.0	mm	
Test Passed	1.5	mm	
Test Passed	2.0	mm	
Toxicity			ABD 0031 (Issue:F), method: AITM 3.0005
Test Passed	1.0	mm	
Test Passed	1.5	mm	
Test Passed	2.0	mm	

OTHER PROPERTIES	VALUE	UNIT	TEST STANDARD
Density	1,00	g/cm ³	EOS Method
Powder Color	white	-	-
Components Color	white	-	-

HEADQUARTERS

EOS GmbH
Electro Optical Systems

Robert-Stirling-Ring 1
82152 Krailling / Munich
Germany

Tel.: +49 89 893 36-0
Email: info@eos.info
URL: www.eos.info

This powder has not been developed, tested or certified as a medical device according to Directive 93/42/EEC (MDD) or Regulation (EU) 2017/745 (MDR) and is not intended to be used as a medical device, in particular for the purposes specified in Art. 2 No. 1 MDR. Insofar as you intend to use the powder as raw material for the manufacture of pharmaceutical products or medical devices (e.g. as raw material which as a material must meet the requirements of Annex 1, Chapter II MDR), the responsibility and liability for all analyses, tests, evaluations, procedures, risk assessments, conformity assessments, approval and certification procedures as well as for all other official and regulatory measures required for this purpose shall lie solely with you both with regard to the pharmaceutical product and/or medical device manufactured by you and with regard to the properties, suitability, testing, evaluation, risk assessment, other requirements for use of the powder as raw material. In this respect, the limitations of liability pursuant to our General Terms and Conditions and the system sales or material contracts shall apply.

Part properties are provided for information purposes only and EOS makes no representation or warranty, and disclaims any liability, with respect to actual part properties achieved. Part properties are dependent on a variety of influencing factors and therefore, actual part properties achieved by the user may deviate from the information stated herein. This document does not on its own represent a sufficient basis for any part design, neither does it provide any agreement or guarantee about the specific properties of a material or part or the suitability of a material or a part for a specific application.

The achievement of certain part properties as well as the assessment of the suitability of this material for a specific purpose is the sole responsibility of the user. Any information given herein is subject to change without notice.

Status as of 03.09.2024. Subject to technical modifications. EOS is certified according to ISO 9001.

EOS®, Additive Minds®, Alumide®, AMQ®, CarbonMide®, DirectMetal®, DMLS®, EOSAME®, EOSINT®, EOSIZE®, EOSPACE®, EOSPRINT®, EOSTATE®, EOSTYLE®, FORMIGA®, LaserProFusion®, PA 2200®, PrimeCast® and PrimePart® are registered trademarks of EOS GmbH Electro Optical Systems in some countries. For more information visit www.eos.info/trademarks.